



MediaJet® PGC 260FD bright white

HIGH GLOSS PHOTO PAPER, FAST DRY, 260,00g/m²

AT A GLANCE

- real PE photo paper
- microporous inkjet coating
- fast drying
- bright white paper
- very consistent layflat
- excellent image sharpness
- largest colour gamut
- printable with pigment and dye inks

SPECIFIC FEATURE:

Universally applicable weighty photo-glossy paper with a high-glossy bright white surface which shows a practically immediate smearless drying and excellent water resistance. Color images are reproduced in an almost photo-realistic way, true colors, living and rich in detail. MediaJet® PGC 260FD bright white is a high-quality photo paper for the universal use on all common LFP inkjet plotters using dye-based as well as pigmented inks. The coating of this genuine photo basic paper shows an excellent color reproduction at high truth of detail, sharpness of outline, an extreme great color complexity and excellent flatness. MediaJet® PGC 260FD bright white is an inkjet paper for highest requirements. The glossy MediaJet® PGC 260FD bright white with high resolution can be laminated cold. Due to its robust surface in many cases lamination is not necessary when used in the indoor area.

PROCESSING:

For optimum printing results, MediaJet® PGC 260FD bright white must be calibrated beforehand on the used printers and with the appropriate ink. Without calibration color modifications can occur. For quality reasons the processing and storage should take place in a climate of about 50% relative humidity and at a temperature of about 23°C. Keep in the original packing carton box and PE-bag at a cool and dry place, clean and dustfree.

TECHNICAL SPECIFICATION:

Application Area:	Nur Im Innenbereich	Surface:	Glaenzend
Material:	Papier	Thickness:	265,00µm
Specific gravity:	260,00g/m ²	Cold lamination:	ja
B1-cert.:	nein	Heat lamination:	ja
can be sewn:		water resistant:	
can be eyeletted:		scratch resistant:	
can be stretched:		Opacity:	96%
Color L:	96,1 Gretag Macbett	Specular gloss:	60 ± 5 %
Color a:	1,4	Whiteness (R457):	96 ± 2 %
Color b:	-9,9	89 Jahre, bei	Lichtintensität 500 [l]
Steifigkeit md	2,3 mN	Optische Dichte, Testbeginn	D= 1.0
Steifigkeit cd	1,3 mN	Testdrucker Epson	Stylus Photo R2400
Display Performance Rating	Lichtbeständigkeit D.		

www.mediajet.de • www.mediajet.at

This information consists of standard values for your guidance. Before using our print media, please check their suitability to your printer and for your intended application. Taking account of technical development, product specifications may be amended without prior notice at any time. There is no guarantee that the same results can be achieved. We can not accept liability for any errors resulting from technical changes in printers and / or inks.